



AQUA HIBRIT TRANS 1002

Aqua Hibrit-1002 is a waterproof product that hybrid polymer based

DESCRIPTION:

Aqua Hibrit-1002 is a waterproof product that hybrid polymer based, isocyanine and solvent-free, silane reinforced, UV absorber and antioxidant contained, transparent, liquid and ready for usage.

ADVANTAGES:

Transparent, does not distort the surface appearance, give brightens.
High mechanical strength.
UV resistant.
Easy implement (by brush, roll and non-air spray).
When applied, it forms a one-piece waterproofing layer that does not cause seams or leaks.
Maintains transparency even years later.
Heat resistance performance over a wide temperature range is between -40 ° C and + 80 ° C.
Even if the waterproofing layer is damaged in any way the damaged part can be easily repaired in a short time.
Resistant to alkali and chemicals.

USAGE AREAS:

Terraces and balconies,
Ceramic surfaces,

Glass surfaces,
Natural stone and concrete surfaces,

TECHNICAL SPESIFICATION :

(23 °C Temperature and 50 % for relative humidity)

Coating Type : One Component Hybrid Polymer

Color : Transparent

Application Temperature : +5 C ile +35 C

Adhesion to Concrate : < 2,00 N/mm2

Application Metod: Roll,Brush,Spray

Dry Time: 6 hours

Coating Again: 8-24 hours

Total Dry : 7 Days

***These values were obtained as a result of laboratory tests, just contain finished applications according to drying time performance. Due to differences in temperature and humidity values in the construction site, the values may change.

APPLICATION METHOD:

Surface Preparation:

The surface; must be cured, dry and durable. Loose surface mortar and such as residues should be cleaned and reached durable surface.

AQUA HIBRIT TRANS 1002

Aqua Hibrit-1002 is a waterproof product that hybrid polymer based

The holes and gaps on the surface, should be repaired with the repair mortar prepared by mixing with **DAYMAN PAIR PLUS** and **DAYMAN EPO MORTAR** or **DAYMAN EPO BOND**.

Corner joints should be chamfered by series of **DAYMAN REPAIR PLUS** or **DAYMAN PAH BAND** with the size of 4x4.

Out corner joints should be broken first and then chamfered.

Preparation Of The Mixture:

The product should be mixed by medium fast 400-600 rpm.mixer until having a homogenous shape.

Application:

The application should be done by brush, trowel or spray,

On the primed surface, the bucket can be immerse or poured, use brush or roll until the surface completely covered, apply minimum two layer,

After the application of the first layer the waiting time must be minimum 8 maximum 24 hours to apply the second layer, Should not be waited more than 48 hours between the layers.

The used instruments should be cleaned in 2 hours after application is done.

ISSUES TO BE CONSIDERED:

If the weather is rainy or possible rainy days the application should not be done,

After the application it must be protected from strong wind, storm and sun in the first 24 hours,

The application should be made on the part of the structure that comes into contact with water.

As the product become slowly cured in the cold weathers, the second coating must be done when the first coating is completely becoming dry.

Ensure that the ambient and floor temperature is between 5 ° C and 30 ° C.

CLEANING OF INSTRUMENTS:

AQUAHIBRIT - 1002 should be cleaned by solvent when it wet.

AQUA HİBRİT-1002 after become dry should be cleaned by the mechanical ways.

CONSUME:

Only for one layer, min.: 0,100-0,500 kg/m²

Total Teoric Consume (for 2 layers) 0, 200 - 1, 00 kg/m²

AQUA HIBRIT TRANS 1002

Aqua Hibrit-1002 is a waterproof product that hybrid polymer based

PACKING:

1, 00 kg

5, 00 kg

COLOR:

Transparent

SHELF LIFE:

Shelf life is 12 months.

Should be stored in the dry and cool are, should be attended to not put under sun or the area that takes direct sun and should be protected from the frost.

Do not stack pallets on top of each other, it should be shipped first in first out.

SAFETY RECOMMENDATIONS:

Wear work clothes, protective gloves, glasses and masks should be used during application.

Do not smoke during the application and work in a well-ventilated place and away from naked flames.

Hands and eyes should be protected by protection equipment.

As cured materials has irritating effect, do not touch with skin and eyes, in case of any

contact rinse with soap and plenty of water, in case of any swallow see doctor urgently.

Food and beverage materials should not be kept in the application area and should not be eaten.

It should be known that the solvent is heavier than air, so remember that it will be on the ground.

Store out of reach of children.

For more information please check the Material Safety Data Sheet.

LIMITATIONS OF LIABILITY:

The information in this technical data sheet is given according to technical information, experience and test result.

As GENERALTÜRK A.Ş. cannot control the usage of the product that used under which kind of conditions, it does not accept any responsibility for the application result and does not guarantee it.

The product suitability for the product user should be tested and decided accordingly.

All products should be considered in the advice of those technical knowledge and equipment.

GENERAL TURK A.Ş can not accept any responsibility that occurs because of miss-




AQUA HIBRIT TRANS 1002

Aqua Hibrit-1002 is a waterproof product that hybrid polymer based

use, it only responsible for the written suggestions that shows the products where and how use.

GENERALTÜRK A.Ş. It may change the properties of its products without announcement.

The technical data sheet is valid until the next time it is printed and all previous technical data sheets invalidate the description / January 2020

 2765	
GENERALTURK TEKNİK YALITIM KİMYA END. SAN. TİC. A.Ş. YUNUSELİ MH. 15. YAVUZ SK. NO: 21 OSMANGAZI - BURSA / TÜRKİYE 20	
2765 - CPR - 0157 EN 1504 - 2	
AQUA HIBRIT TRANS 1002	
PRODUCTS AND SYSTEMS FOR THE PROTECTION AND REPAIR OF CONCRETE STRUCTURES	
Principle 1 (PI): Protection against Ingress, Method 1.3 Coating ©	
Principle 2 (MC): Moisture Control, Method 2.2 Coating ©	
Coating Type	One Component Hybrid Polymer
Adhesion to Concrete	< 2,00 N/mm ²