



CRACK POL WT 815

Polyurethane Epoxy Based Low Viscosity Injection Resin

DESCRIPTION:

It is a two component, low viscosity, closed cell injection resin that reacts with water.

ADVANTAGES:

It stops the water by reacting with it.

Solvent free.

Easy to apply.

It is resistant to weak acids, micro-organisms, alkali and water.

It is flexible and suitable for dilatations.

USAGE AREAS:

Foundations.

Veil.

Retaining walls.

Dams.

Waste water plants.

Cracked walls.

Dilatations.

TECHNICAL SPESIFICATION :

(23 °C Temperature and 50 % for relative humidity)

A Component

Color : Transparent - Yellow

Density 20°C: 1,1 gr/cm3

Application Temperature: +5 - +30 °C

Viscosity : 200 cp

Solid Ratio : 100 %

Shelf Life : 12 months

B Component

Color : Transparent - Yellow

Density 20°C : 1,1 gr/cm3

Viscosity : 15 cp

Application Temperature : +5 - +30 °C

Shelf Life : 12 months

***These values were obtained as a result of laboratory tests, just contain finished applications according to drying time performance. Due to differences in temperature and humidity values in the construction site, the values may change.

APPLICATION METHOD:

Surface Preparation:

The surface; must be cured, dry and durable. Loose surface mortar and such as residues should be cleaned and reached durable surface.

All cracks and joints in the area to be injected should be cleaned.

The cracks larger than 3mm should be covered with suitable repair materials.

The place of the packers is specified according to region where the leakage come from.

CRACK POL WT 815

Polyurethane Epoxy Based Low Viscosity Injection Resin

The packers (injectors) are placed at an angle of 45 degrees.

The packers should be installed at a distance of half the thickness of the reinforced concrete.

The distance between the packers can be between 15 cm and 90 cm.

The dust which inside of the holes should be cleaned.

Preparation Of The Mixture:

Before starting A and B components, should be mixed 400 rpm in its own pack until they reach homogeneous consistency.

Application:

The prepared packers is applied by injection pump.

The application pressure can be vary between 14-200 bars.

The application should be starter from the first packer.

It starts with low pressure to high pressure until the resin overflow.

After the resin overflow should be followed the next packer.

In the injection application, the injected resin will overflow from the reinforce that has leakage from the cracks.

After this application the work is done.

ISSUES TO BE CONSIDERED:

Temperature should be between +5 °C and +30 °C during the application.

CLEANING OF INSTRUMENTS:

CRACK POL WT – 815 should be cleaned by water when it wet.

CRACK POL WT – 815 after become dry should be cleaned by the mechanical ways.

CONSUME:

For 1 lt.gap approx. 0,100 kg.

PACKING:

A component 7, 50 kg.

B component 0, 750 kg.

COLOR:

Blondish, when it swell yellow.

SHELF LIFE:

1 year from the production date under proper storage conditions.

CRACK POL WT - 815 should be stored at temperatures between 5 ° C and 25 ° C.



CRACK POL WT 815

Polyurethane Epoxy Based Low Viscosity Injection Resin

SAFETY RECOMMENDATIONS:

Wear suitable protective clothing, protective gloves, goggles and mask during application.

Do not smoke during application and work in well-ventilated areas away from naked flames.

Hands and eyes must be protected with gloves and protective glasses. In case of contact with material, wash eyes with plenty of water rinse and consult a doctor immediately.

No food or beverage should be allowed in the application area.

Store out of reach of children.

For more information please check the Material Safety Data Sheet

LIMITATIONS OF LIABILITY:

The information in this technical data sheet is given according to technical information, experience and test result.

As GENERALTÜRK A.Ş. cannot control the usage of the product that used under which kind of conditions, it does not accept any responsibility for the application result and does not guarantee it.

The product suitability for the product user should be tested and decided accordingly.

All products should be considered in the advice of those technical knowledge and equipment.

GENERAL TURK A.Ş. can not accept any responsibility that occurs because of miss-use, it only responsible for the written suggestions that shows the products where and how use.

GENERALTÜRK A.Ş. It may change the properties of its products without announcement.

The technical data sheet is valid until the next time it is printed and all previous technical data sheets invalidate the description / January 2020